

## Emittance Measurements Relevant to a 250 W<sub>t</sub> Class RTPV Generator for Space Exploration

Dave Wolford, Donald Chubb, Eric Clark, and Anna Maria Pal Glenn Research Center, Cleveland, Ohio

Dave Scheiman ASRC Aerospace Corporation, Cleveland, Ohio

Jack Colon Sierra Lobo, Inc., Fremont, Ohio

#### NASA STI Program . . . in Profile

Since its founding, NASA has been dedicated to the advancement of aeronautics and space science. The NASA Scientific and Technical Information (STI) program plays a key part in helping NASA maintain this important role.

The NASA STI Program operates under the auspices of the Agency Chief Information Officer. It collects, organizes, provides for archiving, and disseminates NASA's STI. The NASA STI program provides access to the NASA Aeronautics and Space Database and its public interface, the NASA Technical Reports Server, thus providing one of the largest collections of aeronautical and space science STI in the world. Results are published in both non-NASA channels and by NASA in the NASA STI Report Series, which includes the following report types:

- TECHNICAL PUBLICATION. Reports of completed research or a major significant phase of research that present the results of NASA programs and include extensive data or theoretical analysis. Includes compilations of significant scientific and technical data and information deemed to be of continuing reference value. NASA counterpart of peer-reviewed formal professional papers but has less stringent limitations on manuscript length and extent of graphic presentations.
- TECHNICAL MEMORANDUM. Scientific and technical findings that are preliminary or of specialized interest, e.g., quick release reports, working papers, and bibliographies that contain minimal annotation. Does not contain extensive analysis.
- CONTRACTOR REPORT. Scientific and technical findings by NASA-sponsored contractors and grantees.

- CONFERENCE PUBLICATION. Collected papers from scientific and technical conferences, symposia, seminars, or other meetings sponsored or cosponsored by NASA.
- SPECIAL PUBLICATION. Scientific, technical, or historical information from NASA programs, projects, and missions, often concerned with subjects having substantial public interest.
- TECHNICAL TRANSLATION. Englishlanguage translations of foreign scientific and technical material pertinent to NASA's mission.

Specialized services also include creating custom thesauri, building customized databases, organizing and publishing research results.

For more information about the NASA STI program, see the following:

- Access the NASA STI program home page at http://www.sti.nasa.gov
- E-mail your question via the Internet to help@ sti.nasa.gov
- Fax your question to the NASA STI Help Desk at 443–757–5803
- Telephone the NASA STI Help Desk at 443–757–5802
- Write to: NASA Center for AeroSpace Information (CASI) 7115 Standard Drive Hanover, MD 21076–1320

#### NASA/TM-2009-215619



# Emittance Measurements Relevant to a 250 W<sub>t</sub> Class RTPV Generator for Space Exploration

Dave Wolford, Donald Chubb, Eric Clark, and Anna Maria Pal Glenn Research Center, Cleveland, Ohio

Dave Scheiman ASRC Aerospace Corporation, Cleveland, Ohio

Jack Colon Sierra Lobo, Inc., Fremont, Ohio

Prepared for the 5th International Conference on Solar Concentrators for the Generation of Electricity sponsored by the National Renewable Energy Lab Palm Desert, California, November 16–19, 2008

National Aeronautics and Space Administration

Glenn Research Center Cleveland, Ohio 44135

Level of Review: This material has been technically reviewed by technical management. Available from NASA Center for Aerospace Information National Technical Information Service 7115 Standard Drive 5285 Port Royal Road Springfield, VA 22161 Hanover, MD 21076-1320

Available electronically at http://gltrs.grc.nasa.gov

### Emittance Measurements Relevant to a 250 W<sub>t</sub> Class RTPV Generator for Space Exploration

Dave Wolford, Donald Chubb, Eric Clark, and Anna Maria Pal National Aeronautics and Space Administration Glenn Research Center Cleveland, Ohio 44135

Dave Scheiman
ASRC Aerospace Corporation
Cleveland, Ohio 44135

Jack Colon Sierro Lobo, Inc. Fremont, Ohio 43420

#### **Abstract**

A proposed 250 Wt Radioisotope Thermophotovoltaic (RTPV) power system for utilization in lunar exploration and the subsequent exploration of Mars is described. Details of emitter selection are outlined for use in a maintenance free power supply that is productive over a 14-year mission life. Thorough knowledge of a material's spectral emittance is essential for accurate modeling of the RTPV system. While sometimes treated as a surface effect, emittance involves radiation from within a material. This creates a complex thermal gradient which is a combination of conductive and radiative heat transfer mechanisms. Emittance data available in the literature is a valuable resource but it is particular to the test sample's physical characteristics and the test environment. Considerations for making spectral emittance measurements relevant to RTPV development are discussed. Measured spectral emittance data of refractory emitter materials is given. Planned measurement system modifications to improve relevance to the current project are presented.

#### Introduction

NASA and Creare Incorporated of Hanover, New Hampshire are currently engaged in a technology development program of an RTPV power system to be used in lunar exploration missions and the subsequent exploration of Mars. This effort follows prior work by Orbital Sciences Corporation (Ref. 1) and others. Table 1 contains performance details for both the beginning and end (B.O.M. and E.O.M.) of a 10-year mission life. Mass estimates are given for single and dual General Purpose Heat Source (GPHS) configurations. Figure 1 shows an exploded view of the configuration of interest with component parts labeled. The energy source for this configuration is a single GPHS containing plutonia fuel with a B.O.M. thermal output of 250 W.

The efficient conversion of emitted radiation is highly dependent on the temperature of the emitter. This is a combined

effect of the  $T^4$  increase in radiated power (Stefan-Boltzmann law) and a spectral shift towards higher energies as temperature increases (Wien's displacement law). To obtain the maximum efficiency the emitter temperature should be as high as possible. The planned operating temperature for the GPHS module is 1350 K. At this temperature the choice of materials that will not sublimate to cooler surfaces over long time periods is limited. It is desirable that the spectral power reaching the PV array is high for convertible photon energies,  $E > E_g$ , where  $E_g$  is the PV cell bandgap energy. However for the proposed power system, emitter spectral efficiency is secondary to low vapor pressure since evaporation of emitter material on to the cold PV array limits the lifetime of the system.

#### **Emittance Measurement**

Emittance involves radiation from within a material and so becomes more difficult to quantify as the thermal gradient through the material increases (Ref. 2). The emittance data available in the literature is particular to the test sample characteristics and the test environment. The surface quality, material and thermal gradient of the test article must be known to determine if the data can be appropriately applied to a model.

An opaque object's spectral reflectance when measured at an isotropic temperature can be used to determine spectral emittance by Kirchhoff's Law (Ref. 3),  $\epsilon_{\lambda} = \alpha_{\lambda}$  where  $\epsilon_{\lambda} =$  spectral emittance,  $\alpha_{\lambda} =$  spectral absorptance. For conservation of energy,  $\alpha_{\lambda} + \rho_{\lambda} + \tau_{\lambda} = 1$  where  $\rho_{\lambda} =$  spectral reflectance and  $\tau_{\lambda} =$  spectral transmittance. Therefore, since  $\tau_{\lambda} = 0$  for an opaque object,  $\epsilon_{\lambda} = (1 - \rho_{\lambda})$ . This property is often considered intrinsic because the same material will exhibit the same spectral emittance regardless of thickness as long as it is opaque and of the same composition, temperature and surface geometry. However, if the temperature is not isotropic then the spectral emittance will depend on the temperature change through the material.

### TABLE 1.—PERFORMANCE COMPARISON OF SINGLE AND DOUBLE GPHS CONVERTERS AT 15 AND 20 PERCENT EFFICIENCIES

[Mass estimates are conservative, engineering driven improvements are anticipated.]

_	Dual GPHS <sup>a</sup>	Single GPHS	Notes
GPHS mass	3.212	1.606	kg
Converter mass	3.725	2.75	kg
Waste heat radiator mass	4.500	2.425	kg
Total mass	11.440	6.781	kg
Mass specific power at 15% η	6.56	5.53	W/kg
Mass specific power at 20% η	8.74	7.37	W/kg
Power output BOM at 15% η	75.00	37.50	$W_{e}$
Power output BOM at 20% η	100.00	50.00	$W_{e}$
Power output EOM at 15% η	60.04	30.02	W <sub>e</sub> , with 0 material transfer, 10-year mission
Power output EOM at 20% η	80.06	40.03	W <sub>e</sub> , with 0 material transfer, 10-year mission

<sup>&</sup>lt;sup>a</sup>Dual GPHS data (Ref. 6).




Figure 1.—Single GPHS power system, exploded view.

It would be a daunting task to equilibrate a sample at 1350 K and take an accurate reflectance measurement. Instead, a measurement is taken of the spectral emissive power originating from the hot sample and it is referenced to a calibrated blackbody. Figure 2 is a schematic of the Vacuums Emittance Measurement System (VEMS) at NASA, GRC. The system measures the normal spectral emittance,  $\varepsilon_n$  The following is the derivation for the formula used for VEMS data reduction. The spectral radiation flux per wavelength per unit area of an emitter of thickness d and the sample temperature  $T_s$ , measured by the instrument is  $q_{ds}(\lambda, T_s)$ . It is equal to  $F_{es}(\lambda, T_s)$ , where F is a constant and  $e_{s}(\lambda, T_s)$  is the spectral emissive power. Likewise  $q_b(\lambda, T_b)$ , the measured spectral radiation flux of the blackbody at temperature  $T_b$  is  $F_{eb}(\lambda, T_b)$ , where  $e_b(\lambda, T_b)$  is the blackbody emissive power. Therefore,

the constant 
$$F = \frac{q_{db}(\lambda, T_b)}{e_b(\lambda, T_b)}$$
. Since spectral emittance is by

definition the sample's spectral emissive power divided by blackbody emissive power for the same temperature, the result is the following:

$$\varepsilon_{s}(\lambda, T_{s}) = \frac{e_{s}(\lambda, T_{s})}{e_{b}(\lambda, T_{s})} = \frac{q_{d}(\lambda, T_{s})}{F e_{b}(\lambda, T_{s})} = \frac{q_{d}(\lambda, T_{s})e_{b}(\lambda, T_{b})}{q_{d}(\lambda, T_{b})e_{b}(\lambda, T_{s})}$$
(2)

where (ref. 4)

$$e_b(\lambda, T_b) = \frac{2\pi h c_0^2}{\lambda^5 \left[ \exp\left(\frac{hc_0}{\lambda k T_b}\right) - 1 \right]}$$

- h Planck constant
- $c_0$  the speed of light in a vacuum
- k Boltzmann constant

Equation (1) assumes that the temperature of the sample is isotropic. Because of this there is a difficulty applying it to a thermally anisotropic sample.

Radiation that leaves the sample comes not only from the surface but from within the material. Thus, the emissive power and emittance depends on the temperature change across the material. This temperature is determined by the combined effects of thermal conduction and radiation. The temperature dependence is obtained from the solution of the following energy equation.

$$Q_{in=-k_{ih}} \frac{dT}{dx} + Q_{rad(x)}$$
 (2)

Where  $Q_{in}$  is the thermal power unit per unit area,  $k_{th}$  is the thermal conductivity and  $Q_{rad}$  is the total radiative power per unit area at position x. Equation (2) is solved for rare earth materials in Reference 5.




Figure 2.—Diagram of the Vacuum Emittance Measurement System (VEMS) at GRC.

Near the emitting surface the  $Q_{rad}$  term in Equation (2) will dominate and the temperature variation will be nonlinear. However, far from the surface the conduction term in Equation (2) dominates and the temperature variation will be linear.

In Reference (2) the spectral emittance is defined in terms of the temperature of the back (high temperature) side of the emitter. The spectral emittance, assuming a linear temperature variation across the emitter, a large absorptance coefficient and small  $\Delta T$  (the case for most metals) is approximated by the following expression.

$$\varepsilon(\lambda, T_b) = \lceil 1 - R(\lambda) \rceil \exp[\mu_s \Delta T]$$
 (3)

Where R ( $\lambda$ ) is the spectral reflectivity,  $\mu_s$  the dimensionless photonic energy =  $\frac{hc_0}{\lambda kT_s} = \frac{1.439 \times 10^7 \left(K \times nm\right)}{\lambda T_s}$  and

$$\Delta T$$
 = the dimensionless temperature difference =  $\frac{T_b - T_f}{T_b}$ ,

where  $T_b$  is the back side temperature and  $T_f$  is the front side temperature.

Figure 3 shows emittance data calculated using room temperature reflectance data for two tantalum samples of different surface roughnesses. The reflectance was measured using a Perkin-Elmer  $\lambda$  950 dual beam spectrometer. Surface roughness accounts for the apparent difference in measured emittances. The smoother 0.4 mm sample has the lower emittance due to an increased reflectance. Note that this measurement is a total hemispherical measurement.

Figure 4 shows VEMS measurements in addition to the corresponding 1–R curve from Figure 3. This chart illustrates the difficulty of determining emittance using formula (1). Values are shown when calculated using both the cooler front surface




Figure 3.—ɛ= 1—R for two tantalum samples at 300 K, equilibrated temperature.

#### Emittance measurements of tantalum sample c, 0.4 mm, $R_a$ = 222 nm, $\Delta T$ = 258 K




Figure 4.—Emittance data for 0.4-mm-thick tantalum sample,  $\Delta T$  = 258 K.

#### Emittance measurements of tantalum sample a, 3mm, $R_a$ = 659 nm, $\Delta T$ = 287 K




Figure 5.—Emittance data for 3-mm-thick tantalum sample,  $\Delta T = 287$  K.

temperature (top curve) and hot back surface temperature (heavy curve). Temperature measurements were made using 0.005 in. diameter C type tungsten/tungsten-rhenium thermocouples. Contact of the thermocouples to the sample was confirmed electrically by a continuity measurement between the front and back thermocouples. The back surface temperature is not appropriate because even though the metal is closest to this temperature through most of the emitter, radiative cooling dominates near the surface where the emittance takes place. The front surface temperature is an obviously inappropriate value because it produces emittances in excess of one. All emittance occurs in a thickness of approximately one micron, as can be demonstrated by the non-transmitting nature of a film of that thickness. Despite this small dimension, the outer most atoms of the metal are sufficiently cooled by radiation that they do not well represent the temperature through the emitting region. The bottom curve shown is the approximation of emittance using a linear temperature gradient only (formula 3). This curve is in fairly good agreement with emittance calculated using the back surface temperature.

Figure 5 shows the emittance data for the 3 mm thick sample. Of note is the greater difference between the emittance based on  $T_f$  and the emittance based on  $T_b$ . This corresponds to the greater  $\Delta T$  across the sample. Also notice that the formula (3) approximation does not agree with the back temperature as well as with the thinner sample.

#### **Measurement Modifications**

In the optical cavity of a TPV converter, radiation is reflected back to the emitter from the filter-PV array. This radiation will heat the front surface of the emitter and thus reduce the thermal gradient across the emitter. To approximate the conditions that exist in the optical cavity of a TPV system, the VEMS facility is being modified. The objective is to measure the spectral radiation flux of the test sample through an aperture in a chilled plate, which approximates the filter-PV array. A highly polished, gold plated surface facing the emitter would reflect energy back to the sample, thereby raising the front surface temperature and lowering the  $\Delta T$  across the sample. The modified instrument would be able to generate spectral radiation flux data,  $q_s$ , for a given material,  $\Delta T$  and surface geometry, thereby approximating operational conditions for a configuration of interest.

#### Summary

A brief description is given of the goals of the NASA/ Creare RTPV power system development program.

Methods to determine the spectral emittance of system materials in order to model system energy flow are presented.

While emittance measurements are straight forward in thermally isotropic materials, it is difficult when a significant thermal gradient exists through the material of interest. Emittance occurs within a region near the radiating surface that has a severe thermal gradient created by locally dominate radiative heat transfer. Methods dependant on a single temperature value are therefore insufficient. A definition of an emittance must include the temperature variation through the material. A method to reduce temperature gradients is proposed. The spectral radiation flux of the sample,  $q_s(\lambda, T)$ , is measured through a plate that reflects energy back to the test sample. Thus the thermal gradient can be controlled to the anticipated RTPV conditions while  $q_s(\lambda, T)$  is determined. This measurement can be achieved on a 1 to 2 day cycle time in the VEMS facility. This allows for the possibility of rapid emitter optimization.

#### References

- Schock, A. et al., "Modified Design of Radioisotope Thermophotovoltaic Generator to Mitigate Adverse Effect of Measured Cell Voltage," Proceedings of the 31st Intersociety Energy Conversion Engineering Conference, IEEE Catalog No. 96CH35878, Vol. 2, edited by P.Chetty, et al, New Jersey, 1996, pp. 979–994.
- 2. Chubb, D.L., Fundamentals of Thermophotovoltaic Energy Conversion, Elsevier, First edition, 2007 Chapter 3.
- 3. Siegel, Robert, Thermal Radiation Heat Transfer, Hemisphere Publishing Corporation, Second edition, 1981, p. 58.
- 4. Chubb, D.L. et al., "Effect of Temperature on Thick Film Selective Emitter Emittance," *Proceedings of 3rd Conference on Thermophotovoltaic Generation of Electricity*, AIP Conference Proceedings 401, 1997, pp. 293–313.
- Good, B.S. et al., "Temperature Gradient Effects in an Erbium Aluminum Garnett Selective Emitter," 4th NREL Conference on Thermophotovoltaic Generation of Electricity, AIP Conference Proceedings 460, 1999, pp. 214–223.
- 6. Wilt, David et al., "Progress in Radioisotope Thermophotovoltaic System Development," Proceedings of 5th International Energy Conversion Engineering Conference (IECEC), AIAA-2007-4771.

REPORT DOCUMENTATION PAGE		Form Approved OMB No. 0704-0188		
data needed, and completing and reviewing the colle burden, to Department of Defense, Washington Head	mation is estimated to average 1 hour per response, including the time for reviewing instru- ction of information. Send comments regarding this burden estimate or any other aspect of dquarters Services, Directorate for Information Operations and Reports (0704-0188), 1215 any other provision of law, no person shall be subject to any penalty for failing to comply with	this collection of information, including suggestions for reducing this Jefferson Davis Highway, Suite 1204, Arlington, VA 22202-4302.		
1. REPORT DATE (DD-MM-YYYY)	2. REPORT TYPE	3. DATES COVERED (From - To)		
01-08-2009	Technical Memorandum	O. BATES GOVERED (From Fo)		
4. TITLE AND SUBTITLE		5a. CONTRACT NUMBER		
Emittance Measurements Relevent to a 250 W <sub>t</sub> Class RTPV Generator for Space Exploration				
		5b. GRANT NUMBER		
		5c. PROGRAM ELEMENT NUMBER		
6. AUTHOR(S) Wolford, Dave; Chubb, Donald; Clark, Eric; Pal, Anna Maria; Scheiman, Dave; Colon, Jack		5d. PROJECT NUMBER		
		5e. TASK NUMBER		
		5f. WORK UNIT NUMBER WBS 138494.04.03.01		
7. PERFORMING ORGANIZATION NA	ME(S) AND ADDRESS(ES)	8. PERFORMING ORGANIZATION		
National Aeronautics and Space A		REPORT NUMBER		
John H. Glenn Research Center at		E-16935		
Cleveland, Ohio 44135-3191	Edwis 1 idia			
Cleveland, Olilo 44133-3191				
A SPANSODING/MONITODING ACE	NOV NAME(S) AND ADDDESS(ES)	10. SPONSORING/MONITOR'S		
9. SPONSORING/MONITORING AGEI		ACRONYM(S)		
National Aeronautics and Space Administration		NASA		
Washington, DC 20546-0001		INASA		
		11. SPONSORING/MONITORING		
		REPORT NUMBER		
		NASA/TM-2009-215619		
40 DIOTRIPLITION/AVAILABILITY OT	ATPENT			
12. DISTRIBUTION/AVAILABILITY ST	AIEMENI			
Unclassified-Unlimited				
Subject Categories: 20 and 44				
Available electronically at http://gl				
I his publication is available from the NASA	A Center for AeroSpace Information, 443-757-5802			
13. SUPPLEMENTARY NOTES				
	Thermophotovoltaic (RTPV) power system for utilization in			
	Details of emitter selection are outlined for use in a maintena			
	nowledge of a material's spectral emittance is essential for a			
sometimes treated as a surface effect, emittance involves radiation from within a material. This creates a complex thermal gradient which is				
	idiative heat transfer mechanisms. Emittance data available			
	ical characteristics and the test environment. Considerations			
	discussed. Measured spectral emittance data of refractory en			
		uniter materials is given. Flamieu		
measurement system modifications  15. SUBJECT TERMS	s to improve relevance to the current project are presented.			
Emittance; Space exploration				

18. NUMBER OF PAGES

12

17. LIMITATION OF ABSTRACT

UU

c. THIS PAGE

U

16. SECURITY CLASSIFICATION OF:

b. ABSTRACT

a. REPORT U 19a. NAME OF RESPONSIBLE PERSON
STI Help Desk (email:help@sti.nasa.gov)
19b. TELEPHONE NUMBER (include area code)

443-757-5802